

51.125N | Crystal Etch

Total Glass | Crystal Etch

Features

51.125N | Crystal Etch is a high quality polymeric film with the appearance of a crystal glass effect. This PVC film is intended for use in all exterior marking, specially formulated for producing fine window decals. The polymeric film is printable with solvent, eco solvent, latex and UV inks and has excellent cutting and weeding properties. We offer this product in both in 1220mm and 1520mm width rolls.

Technical & Performance Information

Film Thickness 70 microns
Adhesive Thickness 25 microns
Total Thickness 95 microns

Adhesive Type Permanent pressure sensitive acrylic Release Liner 140 gsm PE coated lay flat kraft paper

Artificial Weathering* > 7 years
Film Tensile Strength MD > 45 N/25mm

Film Elongation MD 180 %
Adhesion to steel (20 mins / 180°) 15 N/25mm
Adhesion to steel (24 hrs / 180°) 20 N/25mm
Dimensional Stability < 0.5 mm

Fire Rating Class B. Classification compliant with BS EN 13501-1:2007

Application Temperature $+5 \text{ to } +60 \,^{\circ}\text{C}$ Service Temperature $-30 \text{ to } +110 \,^{\circ}\text{C}$

Groendreef 35 B-9880 Aalter | Belgium T +32 9 216 6700 F +32 9 216 6709

W www.isee2.eu

Warranty

iSee2 warrantees our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrantees our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.

^{*} equivalent to vertical exposure in Mid-European climate